

Марки сталей						
США	Россия	Германия		Англия	Франция	Швеция
AISI	ГОСТ	W.-Nr	DIN	B.S.	AFNOR	SS
304	08X18H10	1.4301	X 5 CrNi 18 9	304 S 15	Z 6 CN 18.09	2332
304 L	03X18H11	1.4306	X 2 CrNi 18 9	304 S 12 304 C 12	Z 2 CN 18.10 Z 2 CN 18.09 Z 3 CN 19.10 M	2352 2333
316		1.4401 1.4436	X 5 CrNiMo 18 10 X 5 CrNiMo 18 10		Z 6 CND 17.11 Z 6 CND 17.12	2347 2343
316 L	03X17H14M2	1.4404 1.4435	X 2 CrNiMo 18 10 X 2 CrNiMo 18 12	316 S 11 316 S 12	Z 2 CND 18.13 Z 2 CND 17.12 Z 3 CND 19.10 M	2348
316 Sb	08X16H13M2Б	1.4580	X 10 CrNiMoNb 18 10	-	Z 6 CNDNb 17.12 Z 6 CNDNb 19.13	-
316 Ti	08X17H13M2T 10X17H13M3T	1.4573	X 10 CrNiMoTi 18 12	320 S 33	-	-
316 Ti	10X17H13M2E	1.4571	X 19 CrNiMoTi 18 10	320 S 17 320 S 31	Z 6 CNDT 17.12	2350
321	12X18H10T	1.4541 1.4878	X 10 CrNiTi 18 9 X 12 CrNiTi 18 9	321 S 12 321 S 20	Z 6 CNT 18.10	2337
410	12X13 15X13Л	1.4006	X 10 Cr 13	410 S 21	Z 12 C 13	2302
420	20X13	1.4021	X 20 Cr 13	420 S 37	Z 20 C 13	2303
430	12X17	1.4016	X 8 Cr 17	430 S 15	Z 8 C 17	2320
431	20X17H2	1.4057	X 22 CrNi 17	431 S 29	Z 15 CN 16.02	2321
A 284 Gr. 0 A 570 Gr. 36;C A 573 Gr. 58	Ст3	1.0116	St.37-3	4360-40 D	E 24-3 E 24-4	1312 1313
1045	Сталь 45	1.0503	C 45	080 M 46	AF 65 C 45	1650
A 48-60 B	СЧ40	0.6040	GG 40	Grade 400	FI 40 D	01 40-00
80-55-06	ВЧ60-2	0.7060	GGG 60	600/3	FGS 600-3	0732-03
Б	Ниобий					
Е	Селен					
М	Молибден					
Н	Никель					
Т	Титан					
Х	Хром					